



Elastomeric Poly-Sealant

TECHNICAL DATA

Specific Gravity at 68°F(20°C).....	1.68
ServiceTemperature Range.....	-75°F to 350°F
Tack Free Time 75°F @50%RH, Minutes.....	30
Viscosity (cps).....	500,000
% Elongation.....	200%
Tensile Strength (psi)	170
Lap Shear (psi).....	210
Hardness Shore A.....	40-45

INSTRUCTIONS FOR USE

Wipe substrates clean to remove any dirt or grease. Remove any old adhesive/sealant. Testing a small area for compatibility is recommended. Apply with standard caulking gun. Any tooling should be done immediately. Cured product may be painted with most industrial and consumer paints.

SHELF LIFE

9 months in closed, original packaging stored at temperatures below 80°F.

PACKAGING

10.1 fl. oz caulking cartridge, 1 gallon, 5 gallon pails, 55 gallon drums.

NOTE: The above technical information is based upon our best knowledge. The end user must test the product with its substrate prior to using it and verify that it is suitable for the application. Our liability is limited to replacement of defective product. We are not responsible for misuse or application specific requirements for which the product is not intended.



6100 South Fairfax Road Bloomington, IN 47401
Toll Free 800-457-1313 Fax 812-824-8185